

ENERGIZER CR1216



Industry Standard Dimensions

mm (inches)



Permissible deflection from a flat.

0.03 (0.001) Minimum Ref. (Applies to top edge of gasket or edge of crimp, whichever is higher.)

Simulated Application test

Typical Performance at 21°C (70°F)

Schedule:	Typical Drains: at 2.85V (mA)	Load (ohms)	Cutoff 2.0V (hours)
Continuous	0.046	62,000	553

Typical Discharge Characteristics



This datasheet contains typical information specific to products manufactured at the time of its publication. Contents herein do not constitute a warranty and are for reference only.

Lithium Coin

Specifications

"Lithium Coin" Lithium / Manganese Dioxide (Li/MnO₂) ANSI-5034LC, IEC-CR1216 3.0 Volts 25 mAh (to 2.0 volts) (Rated at 62K ohms at 21°C) 0.6 grams (0.02 oz.) 0.2 cubic centimeters (0.01 cubic inch) 1 microampere 118 milliwatt hr/g, 413 milliwatt hr/cc 0.008 grams (0.0003 oz.) -30C to 70C ~1% / year

Safety:

Classification: **Chemical System:**

Designation:

Nominal Voltage:

Typical Capacity:

Typical Weight:

Typical Volume:

Energy Density:

Max Rev Charge:

Typical Li Content:

Operating Temp:

Self Discharge:



(1) KEEP OUT OF REACH OF CHILDREN. Swallowing may lead to serious injury or death in as little as 2 hours due to chemical burns and potential perforation of the esophagus. Immediately see doctor; have doctor phone (800) 498-8666.

(2) Battery compartment design. To prevent children from removing batteries, battery compartments should be designed with one of the following methods: a) a tool such as screwdriver or coin is required to open battery compartment or b) the battery compartment door/cover requires the application of a minimum of two independent and simultaneous movements of the securing mechanism to open by hand. Screws should remain captive with the battery door or cover.

Internal Resistance Characteristics

Pulse Test at 21°C (70°F)

IR

20

Bkgnd Drain: Continuous 62K ohms 0.046mA @2.85V

70

60

50

40

30

20

10

n

25

(R, ohms